

March, 2018

3M™ Scotch-Weld™ Low Odor Acrylic Adhesive DP8805NS Green

Product Description

3M™ Scotch-Weld™ Low Odor Acrylic Adhesives are high performance, two-part acrylic adhesives that offer excellent shear, peel, and impact performance. These toughened products provide improved adhesion to many plastics and metals, including those with slightly oily surfaces. These durable products feature a fast rate of strength build, providing structural strength in minutes. Their low odor and non-flammability features also make them easier to incorporate into a manufacturing process.

Review UL File QOQW2. MH17478 and Sign Components Manual (SAM) File E464624 for certification of these adhesive systems in electrical equipment.

Product Features

- Toughened
- Excellent shear strength
- High peel and impact strength
- 10:1 mix ratio control bond line thickness
- Variety of open times available
- Increased cure speed with applied heat
- Contain glass beads (0.010" diameter) to control bond line thickness

Note: Unless otherwise indicated, all properties measured at 72°F (22°C).



Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Uncured Physical Properties

Property	Values	Notes
Base Color	Off-White	
Accelerator Color	Blue	
Base Density	1.06 g/cm ³	Density measured using pycnometer.
Accelerator Density	1.08 g/cm ³	Density measured using pycnometer.
Mix Ratio by Volume (B:A)	10:1	
Mix Ratio by Weight (B:A)	10:1	

Typical Performance Characteristics

Additional Test notes

Note: Environmental aging tests have shown that these adhesives may accelerate the corrosion of certain bare metals (such as cold rolled steel, copper, brass, and bronze), leading to low bond strength values and early bond failure. These adhesives also have relatively low adhesion to low surface energy plastics (such as polypropylene, polyethylene, TPO, and PTFE). Applications involving any of these materials should be carefully evaluated by the end user for suitability.

Note: The presence of oxygen inhibits the cure of acrylic structural adhesives. Therefore, any exposed surfaces of the mixed adhesive will cure much more slowly than adhesive contained within the bond line. With methyl methacrylate (MMA) acrylic adhesives, any uncured adhesive on the surface flashes off immediately, leaving a surface that feels dry to the touch. With these low odor acrylic adhesives, uncured adhesive on exposed surfaces does not evaporate away quickly, leaving a wet film of partially cured material. For manufacturing processes that need a dry surface quickly, such as for subsequent sanding or painting operations, consider instead the standard acrylic adhesives (DP8405NS Green, DP8410NS Green, DP8425NS Green, and Metal Bonder DP8407NS Green).

Bell Peel: 25 lb/in width

Conditions

Dwell/Cure Time: 24 hr @ Room Temperature

Substrate: Aluminum

Failure mode: CF

Methods

ASTM D3167

Additional Information

notes: 1" wide samples; 0.017" bond line thickness; samples pulled at 6 in/min; aluminum surfaces etched; substrates used were 1/16" thick and 0.020" thick aluminum.

Note: The data in this sheet were generated using the 3M™ EPX™ Applicator System equipped with an EPX static mixer, according to manufacturer's directions. Thorough hand-mixing will afford comparable results.

Cohesive Failure (CF), Adhesive Failure (AF), Substrate Failure (SF)

Typical Performance Characteristics (continued)

Overlap Shear Strength	Substrate	Failure mode	Test Condition
3900 lb/in ²	Aluminum	CF	
3500 lb/in ²	Stainless Steel	CF	
2000 lb/in ²	Polyvinyl chloride (PVC)	SF	
1200 lb/in ²	ABS	SF	
1100 lb/in ²	Acrylic (PMMA)	SF	
800 lb/in ²	Polycarbonate (PC)	AF	
400 lb/in ²	Polystyrene Foam	AF	
650 lb/in ²	Fiber Reinforced Polyester	AF	
3300 lb/in ²	FRP (Epoxy)	CF	
800 lb/in ²	Aluminum	AF	-40°F(-40°C)
900 lb/in ²	Aluminum	CF	180°F(82°C)

Property: Overlap Shear Strength

Method: ASTM D1002

Dwell/Cure Time: 1 min open time, 24 cure @ Room Temperature

Surface Preparation: Abraded and Solvent Wiped

notes: 1/2" overlap; 0.010" bond line thickness; samples pulled at 0.1 in/min for metals and 2 in/min for plastics; substrates used were 1/16" thick metals and 1/8" thick plastic. AF: adhesive failure CF: cohesive failure SF: substrate failure

Environmental Resistance (OLS)	Environmental Condition	Substrate
35 %	120°F (49°C) Water	Aluminum
55 %	90°F (32°C) Water	Aluminum
65 %	150°F(66°C) + 80% relative humidity	Aluminum
100 %	-40°F(-40°C)	Aluminum
100 %	300°F(149°C)	Aluminum
70 %	120°F(49°C) + 80% relative humidity	Aluminum
50 %	185°F(85°C) + 85% relative humidity	Aluminum
70 %	Water	Aluminum
75 %	Salt water (5 wt% in water)	Aluminum
95 %	Diesel Fuel	Aluminum
100 %	Motor Oil	Aluminum
85 %	Antifreeze (50 wt% in water)	Aluminum
60 %	Isopropyl Alcohol (IPA)	Aluminum
65 %	Bleach (10 wt% in water)	Aluminum

Table continued on next page

Typical Performance Characteristics (continued)

Environmental Resistance (OLS)	Environmental Condition	Substrate
100 %	-40°F(-40°C)	Polyvinyl chloride (PVC)
100 %	120°F (49°C) + 80% relative humidity	Polyvinyl chloride (PVC)
100 %	150°F (66°C) + 80% relative humidity	Polyvinyl chloride (PVC)
100 %	Water	Polyvinyl chloride (PVC)
100 %	Salt water (5 wt% in water)	Polyvinyl chloride (PVC)
100 %	Hydrochloric acid (16 wt% in water)	Polyvinyl chloride (PVC)
90 %	Sodium hydroxide (10 wt% in water)	Polyvinyl chloride (PVC)
95 %	185°F (85°C) + 85% relative humidity	Polyvinyl chloride (PVC)

Property: Environmental Resistance (OLS)

Method: ASTM D1002

Dwell/Cure Time: 24 hr @ Room Temperature

notes: Values indicate overlap shear test performance retained after 1,000 hours of continuous exposure relative to a control sample left at room temperature.

Note: Fully-cured structural adhesives can withstand short-term incidental contact with almost any solvent, chemical, or environmental condition. However, long-term continuous exposure of these Low Odor Acrylic Adhesives to the following liquids should be avoided: 1. Elevated temperature (>100°F) water 2. Ketone-type solvents (acetone, MEK) 3. Gasoline and similar liquids

Typical Uncured Physical Properties

Property	Values	Notes
Base Viscosity	45,000 cP	Viscosity measured using cone-and-plate viscometer; reported viscosity at 3.8 sec ⁻¹ shear rate.
Accelerator Viscosity	15,000 cP	Viscosity measured using cone-and-plate viscometer; reported viscosity at 3.8 sec ⁻¹ shear rate.

Typical Mixed Physical Properties

Property	Values	Test Condition	Notes
Color	Blue-Green	Mixed	
Viscosity	45,000 cP		
Density (mixed)	1.06 g/cm ³		
Worklife	3 to 5 min	(Nozzle Mixed) @ Room Temperature	Maximum time that adhesive can remain in a static mixing nozzle and still be expelled without undue force on the applicator.

Table continued on next page

Typical Mixed Physical Properties (continued)

Property	Values	Test Condition	Notes
Open Time	4 to 6 min		Maximum time allowed after applying adhesive to one substrate before bond must be closed and fixed in place. Cure times are approximate and depend on adhesive temperature.
Time to Handling Strength	6 to 8 min	Room Temperature	Minimum time required to achieve 50 psi of overlap shear strength. Cure times are approximate and depend on adhesive temperature.
Time to Structural Strength	8 to 10 min		Minimum time required to achieve 1,000 psi of overlap shear strength. Cure times are approximate and depend on adhesive temperature.
Time to Full Cure	24 h	Room Temperature	

Typical Cured Characteristics

Property	Values	Method	Dwell/Cure Time	Notes
Modulus	140,000 lb/in ²	ASTM D638	2 wk @ Room Temperature	1/8" thick Type I test specimens; samples pulled at 0.2 in/min.
Tensile Strength	1,800 lb/in ²	ASTM D638	2 wk @ Room Temperature	1/8" thick Type I test specimens; samples pulled at 0.2 in/min.
Tensile Strain at Break	8.5 %	ASTM D638	2 wk @ Room Temperature	1/8" thick Type I test specimens; samples pulled at 0.2 in/min.

Handling/Application Information

Directions for Use

1. To obtain the highest strength structural bonds, paint, oxide films, oils, dust, mold release agents, and all other surface contaminants must be completely removed. The amount of surface preparation depends on the required bond strength and environmental aging resistance desired by user. For suggested surface preparations on common substrates, see the section on surface preparation.

2. Mixing For Duo-Pak Cartridges

Store cartridges with cap end up to allow any air bubbles to rise towards the tip. To use, simply insert the cartridge into the EPX applicator and start the plunger into the cylinders using light pressure on the trigger. Then remove the cap and expel a small amount of adhesive to ensure material flows freely from both sides of cartridge. For automatic mixing, attach an EPX mixing nozzle to the cartridge and begin dispensing the adhesive. For hand mixing, expel the desired amount of adhesive and mix thoroughly. Mix approximately 15 seconds after obtaining a uniform color.

For Bulk Containers

Mix thoroughly by weight or volume in the proportion specified on the product label or in the typical uncured properties section. Mix approximately 15 seconds after obtaining a uniform color.

3. Apply adhesive and join surfaces within the open time listed for the specific product. Larger quantities and/or higher temperatures will reduce this working time.

4. Allow adhesive to cure at 60°F (16°C) or above until completely firm. Applying heat up to 150°F (66°C) will increase cure speed.

5. Keep parts from moving during cure. Apply contact pressure or fixture in place if necessary. Optimum bond line thickness ranges from 0.005 to 0.020 inch; shear strength will be maximized with thinner bond lines, while peel strength reaches a maximum with thicker bond lines.

6. Excess uncured adhesive can be cleaned up with ketone-type solvents.

*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

Surface Preparation

3M™ Scotch-Weld™ Low Odor Acrylic Adhesives are designed to be used on painted or coated metals, most plastics, glass, and some bare metals. The following cleaning methods are suggested for common surfaces:

Painted/coated metals:

1. Wipe surface free of dust and dirt with clean cloth and pure isopropyl alcohol.*

2. Sandblast or lightly abrade using clean fine grit abrasives. Do not completely remove the paint layer or coating down to bare steel.

3. Wipe again with clean cloth and pure isopropyl alcohol to remove loose particles.*

Aluminum/stainless steel:

1. Wipe surface free of dust and dirt with clean cloth and pure acetone.*

2. Sandblast or lightly abrade using clean fine grit abrasives.

3. Wipe again with clean cloth and pure acetone to remove loose particles.*

Plastics:

1. Wipe surface free of dust and dirt with clean cloth and pure isopropyl alcohol.*

2. Lightly abrade using fine grit abrasives.

3. Wipe again with clean cloth and pure isopropyl alcohol to remove loose particles.*

Glass:

1. Wipe surface free of dust and dirt with clean cloth and pure acetone.*

2. Apply a thin coating of silane adhesion promoter to the glass surface and allow to dry completely before adhesive bonding.

*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

Storage and Shelf Life

Store product at 80°F (27°C) or below. Refrigeration at 40°F (4°C) will help extend shelf life. Do not freeze. Allow product to reach room temperature prior to use. 3M™ Scotch-Weld™ Low Odor Acrylic Adhesives have a shelf life of 24 months from date of manufacture in unopened original containers kept at recommended storage conditions.

Industry Specifications

Review UL File QOQW2. MH17478 and Sign Components Manual (SAM) File E464624 for certification of these adhesive systems in electrical equipment.

3M™ Scotch-Weld™ Low Odor Acrylic Adhesive DP8805NS Green

Family Group

	DP8805NS Green	DP8810NS Green	DP8825NS Green
Time to Full Cure (h) Test Condition: Room Temperature	24	24	24
Tensile Strain at Break (%) Dwell/Cure Time: 2 wk @ Room Temperature	8.5	6.5	Not Tested
Tensile Strength (lb/in ²) Dwell/Cure Time: 2 wk @ Room Temperature	1,800	1,650	Not Tested
Modulus (lb/in ²) Dwell/Cure Time: 2 wk @ Room Temperature	140,000	125,000	Not Tested
Color Test Condition: Mixed	Blue-Green	Blue-Green	Blue-Green

References

- 3m.com Product Page
Url: http://www.3m.com/3M/en_US/company-us/all-3m-products/~/3M-Scotch-Weld-Low-Odor-Acrylic-Adhesive-DP8805NS?N=5002385+3293242480&rt=rud
- Safety Data Sheet
Url: https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=DP8805NS Green

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

Technical Information

The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer

Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

