



TG4040LC

Ultra-Soft Thermal Conductive Pad

Version 2.130218

Ultra-Soft Thermal Conductive Pad

TG4040LC is an ultra-soft, silicone based thermal interface material which has one face naturally tacky and one face dry. TG4040LC has a low thermal impedance, conforms readily to surfaces due to its low hardness and provides a high dielectric breakdown voltage. TG4040LC can be provided in various thicknesses and formats, such as custom die cuts, standard sheets or log rolls depending on the end application.

Features

Excellent thermal conductivity
Great elasticity and elongation
Natural tack on one side; attached film on the other side
Great reworkability
Electrical Insulation
Low oil bleed

Applications

High Power Applications
Electronic components: IC, CPU, MOS
LED, M/B, P/S, Heat Sink
LCD, TV, Notebook PC, PC Telecom Device, Wireless Hub, etc.
DDR II Module, DVD Applications, Hand-set applications, etc.


Properties

✓ REACH Compliant

✓ ROHS Compliant

Property	TG4040LC	Unit	Tolerance	Test Method	
Colour	Blue	-	-	Visual	
	0.3 - 5.0	mm	-	ASTM D374	
Thickness	0.0078 - 0.1969	inch	-	ASTM D374	
Thermal Conductivity	3.5	W/mK	±0.35	ASTM D5470	
Flammability Rating	V-0	-	-	UL 94	
Dielectric Breakdown Voltage	4	kV/mm	±0.4	ASTM D149	
Weight Loss	<0.4	%	-	ASTM E595	
Density	2.6	g/cm³	±0.2	ASTM D792	
Working Temperature	-45 to 200	°C	-	-	
Volume Resistance	>10¹¹	0hm-cm	-	ASTM D257	
Elongation	100	%	-	ASTM D412	
Tensile Strength	60	N/mm²	-	ASTM D412	
Hardness	40	Shore 00	±10	ASTM D2240	
Shelf Life	36	months -		-	
Shelf Life with adhesive (can be requalified for further 12)	12	months	-	-	

Thermal Impedance vs Pressure vs Deflection



T-Global Technology Limited 1 & 2 Cosford Business Park, Central Park, Lutterworth, Leicestershire LE17 4QU U.K.

Tel: +44 (0)1455 553 510

Email: sales@tglobaltechnology.com Web: www.tglobaltechnology.com

Skype: tglobal.technology VAT #: GB 116 662 714




TG4040LC Ultra-Soft Thermal Conductive Pad


Standard Weights & Dimensional Tolerance

	Thickness (mm)	0.50	0.80	1.00	1.50	2.00	2.50	3.00	3.50	4.00	4.50	5.00
	100x100	13.00	20.80	26.00	39.00	52.00	65.00	78.00	91.00	104.00	117.00	130.00
Size	150x150	29.25	46.80	58.50	87.75	117.00	146.25	175.50	204.75	234.00	263.25	292.50
	300x300	117.00	187.20	234.00	351.00	468.00	585.00	702.00	819.00	936.00	1,053.00	1,170.00
	320x320	133.12	212.99	266.24	399.36	532.48	665.60	798.72	931.84	1,064.96	1,198.08	1,331.20

^{*} All measurements in mm

Data





	Thickness (mm)	Tolerance (mm)			
	0.3	±0.03			
	0.5	±0.05 ±0.08 ±0.1 ±0.12			
	0.8				
	1.0				
	1.2				
Die-Cut	1.5	±0.15			
Thickness	2.0	±0.2			
Tolerances	2.5 - 3.5	±0.25			
	4.0 - 4.5	±0.3			
	5.0	±0.35			
	6.0 - 8.0	±0.4			
	9.0	±0.45			
	10.0	±0.5			
	>10.0	±0.5			

NOTICE: The information contained herein is to the best of our knowledge true and accurate. However, since the varied conditions of potential use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part and users should make their own test to determine the suitability of our products in any specific situation. This product is sold without warranty either expressed or implied, of fitness for a particular purpose or otherwise, except that this product shall be of standard quality, and except to the extent otherwise stated in T-Global Technology Europe and North America's invoice, quotation, or order acknowledgment. We disclaim any and all liabilities incurred in connection with the use of information contained herein, or otherwise. All risks of such are assumed by the user. Furthermore, nothing contained herein shall be construed as a recommendation to use any process or to manufacture or to use any product in conflict with existing or future patents covering any product or material or its use.

^{*} Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.