



TGJTC03 Conductive Fabric Tape

Version 2.090218

Conductive Fabric Tape

TGJTC03 is a pressure sensitive adhesive (PSA) tape that has good electrical conductivity in all 3 axes. It has low contract resistance and superior adhesive force, which can shield electromagnetic interference effectively. TGJTC03 can be applied as die cut parts or in roll form. The product is light weight and flexible, providing excellent shielding and corrosion resistance.

Features

Contours to most profiles Flame retardant Extremely durable Corrosion free Can be supplied as die cut parts Sheets or in rolls

Applications

Shielding plastic enclosures Shielding non conductive materials Grounding planes Cable Shielding

Properties

REACH Compliant

ROHS Compliant

Property	TGJTC03	Unit	Tolerance	Test Method
Colour	Grey	-	-	Visual
Thickness	0.03	mm	±0.005	Digital Up- right Gauge
Adhesive Force	Min 800	gf/25mm	-	KS T 1028 (SUS304)
Surface Resistance	∢0.2	Ω/sq	-	Mil DTL 83528C
Top-Bottom Resistance	∢0.2	Ω/in²	-	Mil DTL 83528C
Using Temperature	-30 to 105	°C	-	ASTM D3330
Shelf Life (can be requalified for further 12)	12	months	-	-

T-Global Technology Limited 1 & 2 Cosford Business Park, Central Park, Lutterworth, Leicestershire LE17 4QU U.K.

Tel: +44 (0)1455 553 510 Email: sales@tglobaltechnology.com Web: www.tglobaltechnology.com Skype: tglobal.technology VAT #: GB 116 662 714 **NOTICE:** The information contained herein is to the best of our knowledge true and accurate. However, since the varied conditions of potential use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part and users should make their own test to determine the suitability of our products in any specific situation. This product is sold without warranty either expressed or implied, of fitness for a particular purpose or otherwise, except that this product shall be of standard quality, and except to the extent otherwise stated in T-Global Technology Europe and North America's invoice, quotation, or order acknowledgment. We disclaim any and all liabilities incurred in connection with the use of information contained herein, or otherwise. All risks of such are assumed by the user. Furthermore, nothing contained herein shall be construed as a recommendation to use any process or to manufacture or to use any product in conflict with existing or future patents covering any product or material or its use.