



Zero Charge® Static Dissipative Floor Coating

Dissipative Floor Coating 1720

Introduction

This product is a high gloss floor finish designed for use in electronic production areas, computer rooms and other static sensitive areas. Contains a non-migratory, static dissipative polymer, which will maintain a constant surface resistivity of 10⁶-10⁸ ohms throughout the humidity spectrum.

Features / Benefits

- Zinc Free
- High Gloss
- Slip Resistant
- Effective in Low Humidity
- Zinc Free

Chemical Components

<u>CHEMICAL</u>	<u>CAS #</u>
Potassium Chloride.....	7447-40-7
Acrylate Copolymer	25987-66-0
Dibutylphthalate	84-74-2
Dipropylene glycol methyl ether.....	34590-94-8
Ethanol,2-butoxy-, phosphate.....	78-51-3
2-(2-methoxyethoxy)ethanol	111-77-3
2-propenoic acid, polymer with ethane	9010-77-9
Ethene, homopolymer, oxidized.....	68441-17-8

Specifications

- General Dynamics
- Boeing Aircraft (BAC5485)
- Unisys
- NFPA 56A
- USDA Approved

Instructions

With a new mop and clean pails, apply coating as follows:

1. Apply thin coat to floor, i.e. ¾ way down on the ringer. Let dry to touch, approximately 45 – 60 minutes.
2. Apply a second coat, approximately ½ way down on the ringer.

Note: Two coats only are recommended for conductive tile.

3. If a third coat is applied, wait 24-hour waiting period/dry time after previous coat.

If a third coat is applied, the floor space may be occupied once it is dry. After at least a 6-hour wait, buff the floor with a white pad to harden and polish the coating. Expect a coating yield of 1,200 ft² for each gallon of coating per coat.

Environmental Policy

Techspray® is committed to developing products to ensure a safer and cleaner environment. We will continue to meet and sustain the regulations of all federal, state and local government agencies.

Packaging and Availability

1720-G	1 Gallon in Plastic (coats @1,200 ft ²)
1720-5G	5 Gallons in Plastic (coats @6,000 ft ²)
1720-54G	54 Gallons in Plastic (coats @64,800 ft ²)

Resources

Techspray® products are supported by a global sales, technical and customer services resources.

For additional technical information on this product or other Techspray® products in the United States, call the technical sales department at 800-858-4043, email tsales@techspray.com or visit our web site at: www.techspray.com.

North America
Techspray
P.O. Box 949
Amarillo, TX 79105
800-858-4043
email: tsales@techspray.com

Europe
ITW Contamination Control
Skejby Nordlandsvej 307
DK-8200 Aarhus N
+45 87 400 220
email: info@itw-cc.com

Countries Outside US
Call to locate a distributor
in your country.

Important Notice to Purchaser/User: The information in this publication is based on tests that we believe are reliable. The results may vary due to differences in tests type and conditions. We recommend that each user evaluate the product to determine its suitability for the intended application. Conditions of use are outside our control and vary widely. Techspray's only obligation and your only solution is replacement of product that is shown to be defective when you receive it. In no case will Techspray® be liable for any special, incidental, or consequential damages based on breach of warranty, negligence or any other theory.