

3M™ Novec™ 2701 Electronic Grade Coating

Introduction

3M™ Novec™ 2701 Electronic Grade Coating is a fluorinated polymer solution carried in a hydrofluoroether solvent. Designed for moisture and corrosion protection of printed circuit boards and electronic components, the polymer coating dries to a thin, transparent film with excellent hydrophobic and oleophobic properties. It does not need curing and is easy to apply, remove and repair. Both the solution and polymer are low in toxicity, non-ozone depleting and RoHS compliant. The coating contains a yellow-orange dye that is built into the polymer and designed to fluoresce under UV light to aid the inspection of the coating and quality control of the coating process.

Construction

Solids	Solvent	Color	Container Size
1 wt% fluorinated polymer	3M™ Novec™ 7200 Engineered Fluid	Yellow	3.5 gal (33 lb/15.0 kg), 1 gal (11 lb/5.0 kg)

Typical Physical Properties

Property	Coating Solution
Appearance	Transparent, yellow, liquid solution
Solids	1 wt% fluorinated polymer
Solvent	3M™ Novec™ 7200 Engineered Fluid
Density	1.41 g/mL
Viscosity	0.7 cP
Boiling Point of Solvent	77°C (170°F)
Flash Point	None (per closed cup method)
Environmental System	Low in toxicity, non-ozone depleting, nonflammable, low-VOC, RoHS compliant, contains no chlorine or bromine One part homogeneous solution

Property	Fluoropolymer Coating
Appearance	Transparent, light yellow to orange (depending on thickness)
Coating Thickness	Less than 1 micron (depending on application method)
Solvent and Chemical Resistance	Yes (resists aqueous, hydrocarbon and alcohol based fluids)
T _g (glass transition temperature)	53°C (127°F)
Thermal Stability of Dry Film	Can withstand 175°C for 24 hours and maintain repellency
Contact Angles (static, dip coated/dried on glass substrate)	105° (water), 65° (hexadecane)
Refractive Index	1.3778
Shelf Life	Two years in the original unopened package
Solder-Through Repairability	Yes
Dielectric Constant @30% RH	2.8 (@1kHz)
Dissipation Factor @30% RH	0.011 (@1kHz)
Dielectric Breakdown Strength @35% RH	3700 V/mil

Not for specification purposes. All values @ 25°C unless otherwise specified.

Features

- Easy application and processing – dries in seconds without the need for post-application curing
- Can be easily removed for rework and repair using 3M™ Novec™ Engineered Fluids
- Is UV detectable for easy identification of coating and quality control
- Allows solder-through repairability
- Contains less than 1% volatile organic compounds (VOCs) and has low global warming potential
- Is thermally and electrically stable with good dielectric properties
- Adheres to a variety of materials (metals, glass, ceramics, polymers, composites, laminates)
- Provides excellent repellency, anti-wetting and anti-sticking properties against liquids – water, hydrocarbons, silicones, and photoresists
- Is insoluble in solvents such as heptanes, toluene and water
- The polymer can endure up to 175°C for 24 hours and maintain repellency
- Has low surface energy which allows lubricating oils, silicones, photoresist solutions, etc. to bead and drain freely from coated surfaces
- Has excellent surface wetting, especially under low standoff SMT components
- Protects against corrosive gases and vapors in addition to liquids



Application Ideas

- Provides excellent moisture, chemical and corrosion protection to printed circuit boards and their components
- Provides protection of display and touch panel components
- Is an easy and cost-effective alternative to conformal coatings
- Provides excellent anti-wetting, anti-stiction, anti-migration and anti-corrosion properties in many diverse applications
- Can serve as an anti-corrosion coating for a variety of materials and components

For Additional Information

To request additional product information or sales assistance, contact 3M Customer Service at one of the numbers below or visit www.3M.com/Novec. For other 3M global offices or information on other 3M products for electronics, visit our website at 3M.com/electronics.

Application Techniques

Can be dipped, sprayed or selectively deposited as per the safety and handling requirements stated in the Material Safety Data Sheet (MSDS). Surfaces to be coated should be clean and dry before application. Masking may not be required for larger connector types but testing is always suggested. The solvent will evaporate quickly and the fluorochemical polymer film will dry in minutes.

Application Options	Dipping (preferred), spray, syringe dispense
Dilution	Can be diluted with 3M™ Novec™ 7200 Engineered Fluid
Drying/Curing	Dries at room temperature; can be handled in under two minutes
Removability	Removable with a variety of 3M Novec Engineered Fluids

Safety, Handling, Storage, Shelf Life

To avoid thermal decomposition, the coating solution should not be heated above 150°C (302°F) and the dried fluorochemical polymer film should not be heated to temperatures above 250°C (482°F). Please note that we do not recommend open, manual spraying of the material. Use of automated/robotic equipment that is enclosed and vented is highly suggested. Contact 3M for equipment vendor suggestions. When stored under conditions of 16-27°C (60-80°F) and less than 60% R.H. in the original, unopened container, the shelf life is certified for 2 years from date of manufacture. Before using this product, please read the current product Safety Data Sheet (available through your 3M sales or technical service representative or at www.3M.com/Novec) and the precautionary statement on the product package. Follow all applicable precautions and directions. Always practice smart and safe industrial hygiene practices.

Coating Inspection

This polymer contains a dye that is both visible (yellow) and fluoresces under UV light to aid in the identification and quality control of the coating process. The dye is reacted into the backbone of the polymer. It will not migrate or off-gas from the polymer film. Inspection of the polymer under a range of UV frequencies can be accomplished with commercially available UV lamps designed for industrial use. The dye fluoresces brightest under higher frequency UV (254 nm) but will also fluoresce at other common UV frequencies (i.e. 310, 365 nm). Please follow the UV lamp manufacturer's recommendations on safe handling of UV radiation. Fluorescence of the polymer will depend on several factors including coating thickness; substrate type and color; UV source frequency, intensity and distance from the coating surface.

The 3M™ Novec™ Brand Family

The Novec brand is the hallmark for a variety of proprietary 3M products. Although each has its own unique formula and performance properties, all Novec products are designed in common to address the need for safe, effective, sustainable solutions in industry-specific applications. These include precision and electronics cleaning, heat transfer, fire protection, protective coatings, immersion cooling, advanced insulation media replacement solutions and several specialty chemical applications.

3M™ Novec™ Engineered Fluids • 3M™ Novec™ Aerosol Cleaners • 3M™ Novec™ 1230 Fire Protection Fluid • 3M™ Novec™ Electronic Grade Coatings • 3M™ Novec™ Electronic Surfactants • 3M™ Novec™ Dielectric Fluids

United States	China	Europe	Japan	Korea	Singapore	Taiwan
3M Electronics Materials Solutions Division 800 810 8513	3M China Ltd. 86 21 6275 3535	3M Belgium N.V. 32 3 250 7521	3M Japan Limited 81 3 6409 3800	3M Korea Limited 82 2 3771 4114	3M Singapore Pte. Ltd. 65 64508888	3M Taiwan Limited 886 2 2704 9011

Regulatory: For regulatory information about this product, contact your 3M representative.

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer: Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.



Electronics Materials Solutions Division

3M Center, Building 224-3N-11
St. Paul, MN 55144-1000
www.3M.com/novec
1-800-810-8513

Please recycle. Printed in USA.
© 3M 2016. All rights reserved.
Issued: 5/16 11583HB
60-5002-0612-7

3M and Novec are trademarks of 3M Company.
Used under license by 3M subsidiaries and affiliates.