

3M™ Novec™ 2702 Electronic Grade Coating

Introduction

3M™ Novec™ 2702 Electronic Grade Coating is a clear, low viscosity, low surface tension solution of a fluorochemical polymer coating carried in a hydrofluoroether solvent. Designed for moisture and corrosion protection of printed circuit boards and electronic components, it dries to a thin, transparent, permanent film with excellent hydrophobic and oleophobic properties. Easy to apply, the coating should be post-cured to provide added durability and abrasion resistance. It is non-flammable, low in toxicity, non-ozone depleting and RoHS compliant.

Construction

Solids	Solvent	Color	Container Size
2 wt% fluoropolymer	3M™ Novec™ 7200DL Engineered Fluid	Clear	2.8 gal (33lb/15 kg), 1 gal (12lb/5.4 kg)

Typical Physical Properties

Property	Coating Solution
Appearance	Clear, colorless liquid solution
Solids	2 wt% fluoropolymer
Solvent	3M™ Novec™ 7200DL Engineered Fluid
Specific Gravity	1.43
Boiling Point of Solvent	76°C (168.8°F)
Flash Point	None
Environmental	Low in toxicity, non-ozone depleting, non-flammable, VOC exempt (US EPA), RoHS compliant, contains no chlorine or bromine
System	One Part

Not for specification purposes. All values @ 25°C unless otherwise specified.

Property	Fluoropolymer Coating
Appearance	Transparent, colorless
Coating Thickness	100 nm - 1 µm (depending on application method)
Solvent and Chemical Resistance	Yes
T _g (glass transition temperature)	-63°C (-145.4°F)
Thermal Stability of Dry Film	Less than 5% weight loss after 1 hour at 200°C in air
Contact Angles (static, dip coated/dried on glass substrate)	105° (water), 65° (hexadecane)
Refractive Index	1.41
Shelf Life	2 years from date of manufacture in unopened container
Solder-Through Repairability	Yes
Nonflammability	Meets UL 94 V-0
Dielectric Constant @30% RH	3.45 (@ 10Hz), 3.04 (@ 1 kHz), 2.61 (@ 1 MHz)
Dissipation Factor @30% RH	0.05 (@ 10Hz), 0.04 (@ 1 kHz), 0.03 (@ 1 MHz)
Dielectric Breakdown Strength @20°C, 30% RH"	1500 V/mil (20°C, 30%RH)

Features

- Low surface tension of the coating solution provides increased surface wetting, especially under low profile components
- Cross-links with a thermal cure for durable protection
- Contains no volatile organic compounds (VOCs) and has low global warming potential
- Can be applied to metals, glass or epoxy laminates
- Provides excellent repellency, anti-wetting and anti-sticking properties against liquids – water, hydrocarbons, silicones, and photoresists
- Is insoluble in solvents such as heptane, toluene and water
- Is thermally and electrically stable with excellent dielectric properties
- Covalently bonds to glass and metal oxide layers
- The polymer can endure up to 200°C for prolonged periods and maintain good repellency
- Has low surface energy which allows lubricating oils, silicones, etc. to bead and drain freely from coated surfaces



Application Ideas

- Provides excellent moisture, chemical and corrosion protection to printed circuit boards and their components
- Is an easy and cost effective alternative to conformal coatings
- Can be used as a durable hydrophobic or oleophobic surface treatment in many diverse applications
- Can serve as
 - an anti-stiction coating for liquid crystal displays, micromotors or MEMS (Micro Electronic Mechanical Systems) components
 - an anti-migration coating for displays, spindle motors or lubricated electronic parts or
 - an anti-corrosion coating for a variety of materials and components

Application Techniques

Can be dipped, sprayed or selectively deposited. Water should be kept out of coating bath as contact will decrease the pot life. Surfaces to be coated should be clean and dried before application. Masking may not be required for many connector types but testing is suggested. The solvent will evaporate quickly and the fluoropolymer film will dry in minutes. The coating should be thermally cured in an oven for best results.

Application Options	Dipping (preferred), spray, syringe dispense
Dilution	Can be diluted with 3M™ Novec™ 7200DL Engineered Fluid
Drying/Curing	Air dried in 30-90 seconds; Cure at 75-150°C for 30-90 minutes
Removability	Permanent once cured

Safety, Handling, Storage, Shelf Life

To avoid thermal decomposition, the coating solution should not be heated above 150°C (302°F) and the dried fluoropolymer film should not be heated to temperatures above 250°C (482°F). When stored under conditions of 16-27°C (60-80°F) and less than 60% R.H. in the original, unopened container, the shelf life is certified for two years. Before using this product, please read the current product Material Safety Data Sheet (available through your 3M sales or technical service representative or at www.3M.com/Novec) and the precautionary statement on the product package. Follow all applicable precautions and directions.

For Additional Information

To request additional product information or sales assistance, contact 3M Customer Service at one of the numbers below or visit www.3M.com/Novec. For other 3M global offices or information on other 3M products for electronics, visit our web site at 3M.com/electronics.

The 3M™ Novec™ Brand Family

The Novec brand is the hallmark for a variety of patented 3M compounds. Although each has its own unique formula and performance properties, all Novec products are designed in common to address the need for safe, effective, sustainable solutions in industry-specific applications. These include precision and electronics cleaning, heat transfer, protective coatings and surface modifiers, fire protection, lubricant deposition and several specialty chemical applications.

3M™ Novec™ Engineered Fluids • 3M™ Novec™ Aerosol Cleaners • 3M™ Novec™ 1230 Fire Protection Fluid • 3M™ Novec™ Electronic Grade Coatings • 3M™ Novec™ Electronic Surfactants

United States	China	Europe	Japan	Korea	Singapore	Taiwan
3M Electronics Markets Materials Division 800 810 8513	3M China Ltd. 86 21 6275 3535	3M Belgium N.V. 32 3 250 7521	Sumitomo 3M Limited 813 3709 8250	3M Korea Limited 82 2 3771 4114	3M Singapore Pte. Ltd. 65 64508888	3M Taiwan Ltd. 866 2 2704 9011

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer: Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.



Electronics Markets Materials Division

3M Center, Building 224-3N-11
St. Paul, MN 55144-1000
www.3M.com/novec
1-800-810-8513

Please recycle. Printed in USA.
© 3M 2013. All rights reserved.
Issued:10/13 7981HB
60-5002-0517-8

3M and Novec are trademarks of 3M Company.
Used under license by 3M subsidiaries and affiliates.