

Advanced Materials**Araldite® 2033**

Structural Adhesives

Technical Data**Araldite® 2033****Two component gap filling epoxy adhesive with flame retardant properties****Key properties**

- Self extinguishing
- UL 94 V-0
- Gap filling
- Medium open time
- High strength

Description

Araldite® 2033 is a room temperature curing self extinguishing epoxy adhesive, consisting of a black resin component and a white-coloured hardener component. It is a rigid adhesive suitable for structural applications and giving high strength on metals.

Product data

Property	Component A (resin)	Component B (hardener)	Mixed Adhesive
Colour (visual)	Black	White	Black
Specific gravity	1.4	1.2	1.3
Viscosity at 25°C (Pas)	Thixotropic paste	Thixotropic paste	Thixotropic paste
Pot Life (100 gm at 25°C)	-	-	120 - 140 minutes
Work time in static mixer			ca. 120 minutes

Processing**Pretreatment**

The strength and durability of a bonded joint are dependent on proper treatment of the surfaces to be bonded. At the very least, joint surfaces should be cleaned with a good degreasing agent such as acetone, iso-propanol (for plastics) or other proprietary degreasing agents in order to remove all traces of oil, grease and dirt. Low grade alcohol, gasoline (petrol) or paint thinners should never be used. The strongest and most durable joints are obtained by either mechanically abrading or chemically etching ("pickling") the degreased surfaces. Abrading should be followed by a second degreasing treatment

Mix ratio	Parts by weight	Parts by volume
Component A (resin)	100	100
Component B (hardener)	88	100

Araldite® 2033 is available in cartridges incorporating mixers and can be applied as ready to use adhesive with the aid of the tool recommended by Huntsman Advanced Materials.

Application of adhesive

The resin/hardener mix may be applied manually or robotically to the pretreated and dry joint surfaces. Huntsman's technical support group can assist the user in the selection of a suitable application method as well as suggest a variety of reputable companies that manufacture and service adhesive dispensing equipment.

A layer of adhesive 0.05 to 0.10 mm thick will normally impart the greatest lap shear strength to the joint. Huntsman stresses that proper adhesive joint design is also critical for a durable bond. The joint components should be assembled and secured in a fixed position as soon as the adhesive has been applied.

For more detailed explanations regarding surface preparation and pretreatment, adhesive joint design, and the dual syringe dispensing system, visit www.araldite2000plus.com.

Equipment maintenance

All tools should be cleaned with hot water and soap before adhesives residues have had time to cure. The removal of cured residues is a difficult and time-consuming operation.

If solvents such as acetone are used for cleaning, operatives should take the appropriate precautions and, in addition, avoid skin and eye contact.

Times to minimum shear strength (laboratory conditions: 40-60% RH)

Temperature	°C	10	15	23	40	60	100
Cure time to reach	hours	14	8	4			
LSS > 1MPa	minutes				85	15	< 5
Cure time to reach	hours	46	26	10	2.5		
LSS > 10MPa	minutes					40	8

LSS = Lap shear strength.

Typical cured properties

Unless otherwise stated, the figures given below were all determined by testing standard specimens made by lap-jointing 114 x 25 x 1.6 mm strips of aluminium alloy. The joint area was 12.5 x 25 mm in each case.

The figures were determined with typical production batches using standard testing methods. They are provided solely as technical information and do not constitute a product specification.


Average lap shear strengths of typical metal-to-metal joints (ISO 4587)

Cured for 16 hours at 40°C and tested at 23°C

Pretreatment - Sand blasting


Average lap shear strengths of typical plastic-to-plastic joints (ISO 4587)

Cured for 16 hour at 40°C and tested at 23°C. Pretreatment - Lightly abrade and alcohol degrease.



Lap shear strength versus temperature (ISO 4587) (typical average values)

Cure: 16 hours at 40°C



Glass transition temperature

Cure: 16 hours at 40°C

69°C by DMA

Tensile strength at 23°C (ISO 527)

20 MPa

E- Modulus

576 MPa

Elongation at break

39 %

Shear modulus (ISO 6721)

-40°C

2.52 GPa

0°C

2.05 Gpa

60°C

205 MPa

100°C

36 Mpa


Thermal cycling

Lap shear strength after 100 cycles of 6 hours duration from -30°C to 70°C

18.8 MPa

Lap shear strength versus immersion in various media at 23°C (typical average values)

Cure 16 hours at 40°C




Lap shear strength versus tropical weathering

(40/92, DIN 50017; typical average values)


Cure: 16 hours at 40°C

Test: at 23°C



Lap shear strength versus heat ageing

Cure: 16 hours at 40°C



Flamability**Flamability test UL94**

Test Method	Thickness	Value
IEC 60695-11-10	4.5 mm	V-0

Storage

Araldite 2033 may be stored for up to 1 year at room temperature, provided the components are stored in sealed containers. The expiry date is indicated on the label.

Handling precautions**Caution**

Our products are generally quite harmless to handle provided that certain precautions normally taken when handling chemicals are observed. The uncured materials must not, for instance, be allowed to come into contact with foodstuffs or food utensils, and measures should be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The wearing of impervious rubber or plastic gloves will normally be necessary; likewise the use of eye protection. The skin should be thoroughly cleansed at the end of each working period by washing with soap and warm water. The use of solvents is to be avoided. Disposable paper - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. These precautions are described in greater detail in the Material Safety Data sheets for the individual products and should be referred to for fuller information.

Filename: Araldite 2033_eur_e
Directory: \\specialties\dfs\Homefolders_BEBE\H96654\Desktop
Template: \\specialties.int.huntsman.com\dfs\AppData_BEBE_002\H96654
 \Application Data\Microsoft\Templates\Normal.dot
Title: Technical Data
Subject:
Author: Donna Hart
Keywords:
Comments:
Creation Date: 1/5/2010 9:49 AM
Change Number: 18
Last Saved On: 1/5/2010 5:29 PM
Last Saved By: h89333
Total Editing Time: 38 Minutes
Last Printed On: 1/6/2010 4:40 PM
As of Last Complete Printing
 Number of Pages: 6
 Number of Words: 975 (approx.)
 Number of Characters: 5.563 (approx.)