



401 N. Raddant Rd.
 Batavia, IL 60510
 ph: 630-761-8900
 fx: 630-761-8989

Technical Data Sheet Cybercryl 1094

www.cyberbond1.com
 "The Power of Adhesive Information"™

Product Description

Cybercryl 1094 is a highly reactive surface activator designed to speed cure rates of Titan anaerobic adhesives. Cybercryl 1094 is designed for use in bonding applications where speed is essential. Cybercryl 1094 can also act as a cleaner where surface preparation is impossible.

Physical Properties

Liquid

Base Compound	Acetone
Appearance	Green Liquid
Viscosity (cP @ 68°F)	2 cP
Density (g/cc)	0.786
Flash Point (TCC)	-4°F
Shelf Life @40°F	12 months unopened
Boiling Point	210°F
Odor	Pungent

Military Specifications

Mil-S-22473E
 Grade N, Form R

General Instructions

Surfaces to be bonded should be clean and dry. Spray or wipe Cybercryl 1094 onto metal surface prior to applying Titan anaerobic adhesive.

Health Precautions:

Cybercryl 1094 is highly reactive and should be stored away from heat, open flame, or ignition sources. Keep containers tightly closed. Use in a well ventilated area. Wash exposed areas with copious amounts of soap and water for at least 15-20 minutes. Contact a physician. Consult msds prior to use.

Storage

Products should be stored unopened in a cool, dry place out of direct sunlight. Shelf life of Cybercryl 1094 is 12 months when properly stored in original containers.

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS)

NOTE

The data contained herein are furnished for information only and are believed to be reliable. Cyberbond L.L.C. cannot assume responsibility for the results obtained by others over whose method Cyberbond L.L.C. does not control. It is the user's responsibility to determine suitability for the product or of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Cyberbond L.L.C. specifically disclaims all warranties of merchantability or fitness for a particular purpose arising from sale or use of Cyberbond L.L.C. products. Cyberbond L.L.C. specifically disclaims any liability for consequential or incidental damages of any kind, including loss of profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Cyberbond L.L.C. patents which may cover such processes or compositions. We recommend that each prospective user test the proposed application to determine its suitability for the purpose intended prior to incorporating any product or application in its manufacturing process using the data as a guide.

NOT FOR PRODUCT SPECIFICATIONS. THE DATA CONTAINED HEREIN ARE INTENDED AS REFERENCE ONLY. PLEASE CONTACT CYBERBOND L.L.C. TECHNICAL DEPARTMENT FOR ASSISTANCE AND RECOMMENDATIONS.

CYBERBOND L.L.C. BATAVIA, IL 60510 PHONE: 630-761-8900 FAX: 630-761-8989