

Trade Name: **SJM-40W NH(IMT)**

1. Company Address: Almit GmbH Ph.: +49 6061 96925-0
 Unterer Hammer 3 Fax: +49 6061 96925-18
 (D) 64720 Michelstadt - near Frankfurt

2. Validity: This specification is specified for:
 Almit-Solder-Paste SJM-40W NH(IMT)
 Delivered by Almit GmbH to: _____

3. Diameter & Allowance:

Weight	500g	500g	700g	1000g	0
Allowance	-0, +10g				

4. Deliverable Reel Size:

Metal Name	Solidus °C	Liquidus °C	Specific Gravity
SJM-40	221	227	7.4

5. Physical Properties:

Test	Characteristics	Test Methods
Metal Content	88.0 ± 1.0	IPC-TM-650 2.2.20
Silver Chromate	pass	IPC-TM-650 2.3.33
Copper Mirror Test	pass	IPC-TM-650 2.3.32
SIR (85°C, 85%, 168hr) (Ω)	≥ 1x10 ⁸	IPC-TM-650 2.6.3.3
Corrosion Test	pass	IPC-TM-650 2.6.15
Flux materials composition	RO	J-STD-004B
Quantitative Halide	LO < 0.0%	IPC-TM-650 2.3.28.1
Fluorides By Spot Test	pass	IPC-TM-650 2.3.35.1

6. Characterisitcs:

Composition	Components						
	Sn	Ag			Sb	Bi	Si
Standard	Rest	4.0			3.0	2.0	≤0.25
Composition	Components						
Standard							

7. Solder Powder Size & Distribuon:

% of Sample by Weight – Nominal Size

Type	not larger than	less than 1% larger than	at least 80% between	at most 10% less than
Type 4 (W)	40 Microns	38 Microns	20 - 38 Microns	20 Microns

8. Lot-Size: A single lot contains 500kg which is the amount of one melting.

9. Quality and Inspecon:

Inspecon items are applied to each lot as follows:

Test No.	Inspection Item	Contents	Standard		
1	Appearance	Color	Comparison with Limit Specimen		
2	Weight	Net Weight	-0 ; +10	(g)	
3	Solder Powder Size	20 - 38 μ m (W)	94 \leq	(wt%)	
4	Metal Composition	Sn	Rest	(wt%)	
		Ag	4.0 \pm 0.2	(wt%)	
		Bi	2.0 \pm 0.2	(wt%)	
		Sb	3.0 \pm 0.2	(wt%)	
5	Characteristics	Flux Content	12.0 \pm 0.5	(wt%)	
6		Solder Balling Test	Comparison with Limit Specimen		
7		Viscosity (Spiral type, 10rpm, 25°C) (IPC-650-2.4.34.3)	210000 \pm 30000 210 \pm 30	(cps)	(Pa•s)
8		Solderability on Cu-Plate	Comparison with Limit Specimen		
9		Dryness	Chalk powder should be easily removed from each test specimen.		

*Straight lines of solder paste are printed on a JIS-2 type substrate then reflowed. The reflowed solder is examined with a stereo microscope at 30X magnification. No more than 2 solder balls larger than one fifth the size of the pattern gap is allowed per gap.

10. Packing:

Individual Package		Outer Package	
Unit	Packing	Unit	Packing
500g	Polyethylene bottle	10kg ; 20kg	Cardboard Box
500g	6 oz Cartridge	10kg	
700g	Proflow Cassette	7kg ; 14kg	
1000g	12 oz Cartridge	15kg	

11. Identification:

	Polyethylene bottle	Cardboard
Name	Almit-Solder-Paste SJM-40W NH(IMT)	same as the left
Lot Nr.	(Ex.) 120119-9	dto.
Solder Powder Size	20 - 38 μ m	dto.
Date of Mfg.	(Ex.) 19.01.2012	dto.
Net Weight	(Ex.) 500g	dto.
Maker	Nihon Almit Co. Ltd.	dto.

10. Maker Address:

Nihon Almit Co. Ltd.
Almit Bldg., 2-14-2 Yayoicho, Nakano-ku, Tokyo, Japan

11. In case of changing this specification it should be accepted by:

Signature_____ Date_____

12. This product is manufactured, using all guaranteed materials according to the legal law regulations.

13. Shelf Life:

Up to 6 months from the manufactured date (lot number).