



N800AH 非矽型導熱片

Non-Silicone Thermal Conductive Pad

Property	N800AH	TEST METHOD	UNIT
Color	Pink	Visual	-
Surface tack 2-side/1-side	2	-	-
Thickness	Customized	ASTM D374	mm
Density	3.3	ASTM D792	g/cm ³
Hardness	60	ASTM D2240	Shore OO
Application temperature	-60~125	-	°C
COMPRESSION@1.0mm			
Deflection @10 psi	15	ASTM D5470 modify	%
Deflection @20 psi	40	ASTM D5470 modify	%
Deflection @30 psi	68	ASTM D5470 modify	%
ELECTRICAL			
Dielectric breakdown	8	ASTM D149	KV/mm
Surface resistivity	>10 ¹¹	ASTM D257	Ohm
Volume resistivity	>10 ¹⁰	ASTM D257	Ohm-m
THERMAL			
Thermal Conductivity	7.0	ASTM D5470	W/m*K
Thermal impedance@10 psi	0.27	ASTM D5470	°C-in ² /W
Thermal impedance@20 psi	0.18	ASTM D5470	°C-in ² /W
Thermal impedance@30 psi	0.12	ASTM D5470	°C-in ² /W

Note:

All specifications provided by LiPOLY are subject to change without notice. The test methods used by LiPOLY are based on the TIM Tester method and ASTM D5470 test method. These test methods are used as the definition standards for LiPOLY. Property values provided in this document are not for product specifications or guaranteed. This document does not guarantee the performance and quality required for the purchaser's specific purpose. The purchaser needs to evaluate and verify the safety before using the material. We strongly recommend the purchaser pre-test the product and verify the performance of the product under the purchaser's specific conditions. Liability and use of the product are the responsibility of the end user. LiPOLY makes no warranty as to the suitability, merchantability, or non-infringement of any LiPOLY material or product for any specific or general uses. LiPOLY shall not be liable for incidental or consequential damages of any kind. All LiPOLY products are sold in accordance with the LiPOLY Terms and Conditions in effect at the time of purchase and a copy of which will be furnished upon request. All rights reserved, including LiPOLY trademarks or registered trademarks of LiPOLY or its affiliates. Statements concerning possible or suggested uses made herein shall not be relied upon or be constructed as a guaranty of patent infringement. Copyright 2019 LiPOLY.