


## VieTape HT9002



- **Facestock**
- **Adhesive**
- **Liner**



### PERFORMANCE FEATURES

Physical Properties	Values
<b>FACESTOCK</b>	
Type	Direct thermal paper (Top-coated)
Basic Weight	65 f 3g/m <sup>2</sup>
Caliper	60 f 5μm
<b>GENERAL CHARACTERISTICS:</b>	
<p>This product is designed for use in direct thermal printing systems at various printing speeds. Typical applications include barcode labels for typical weight scale applications where moderate to high barcode image is required. A product designed with essential resistance to oil, water and heat suited for pre-packed food. It is advisable to test the product with the end-use conditions during the qualification to ensure it meets specific requirements.</p> <p>Suggestion: don't use on PVC or softer type of surfaces.</p>	
<b>ADHESIVE</b>	
Type	Permanent hot melt adhesive
Initial Tack Glass	>=8N/25mm
Adhesion to Stainless Steel	>=15N/25mm
Thickness	18 f 2μm
Minimum Application Temperature	8×C
Service Temperature	-15×C to 60×C subject to facestock limitations

VIETAPE MATERIAL TECHNOLOGY CO., LTD

18F Tang Nhon Phu Street, Phuoc Long B District,  
Thu Duc City, Ho Chi Minh City, Vietnam

info@vietape.com  
(+84) 869 681 639

www.vietape.com



FDA Compliant : US FDA 21 CFR 175.105 (Adhesive) for indirect food contact packaging & processing

Shelf Life : 1 years if store in 23oC and 50% RH condition. The product must be stored in shady or cool place and not be exposed to sunlight directly

**LINER**

Type	White glassine paper
Basic Weight	58 f 3g/m2
Caliper	52 f 5µm
Color	White

**GENERAL CHARACTERISTICS:**

High density and good transparency.

Excellent resistance in die-cut pressure.

All product properties are measured in accordance with Pressure Sensitive Tape Council and/or ASTM test methods. The physical properties listed above are typical values and are not to be construed as specifications. Our suggestions and recommendations for use are based on tests we believe to be reliable. However, the purchaser must determine the suitability of the product for his intended use. We assume no liability for claims beyond the replacement value of our product proved to be defective. Note: Tape should be stored in its original packaging in a cool, dry area (60 F to 80 F and 50% relative humidity) away from direct sunlight. Tape should be used within 12 months from the date of shipment. Application surfaces should be clean, dry and free of grease, oil or other contaminants.

**VIETAPE MATERIAL TECHNOLOGY CO., LTD**

18F Tang Nhon Phu Street, Phuoc Long B District,  
Thu Duc City, Ho Chi Minh City, Vietnam

info@vietape.com  
(+84) 869 681 639

www.vietape.com

