


VieTape TSI-3601S

Polyimide Film

PRODUCT FEATURES

- High-performance adhesive resists and provides a no-residue removal.
- Anti-static version: provide high electrostatic dissipation
- Generally used in masking applications for electronic component and printed circuit board production.
- 12-month shelf life
- Can be attached to the Fluoride separation film



PERFORMANCE FEATURES

| Physical Properties | Values |
|---------------------------------|-------------------|
| Color | Amber |
| Backing Thickness | 0.025 mm |
| Adhesive Thickness | 0.035 mm |
| Adhesion to Steel (PSTC-101) | 6.5 N/25mm width |
| Tensile Strength (PSTC-31) | 115 N/25 mm width |
| Elongation (PSTC-31) | 50% |
| Breakdown voltage (PSTC-51) | 4.5 kV |
| Anti-static level (ASTM D 3759) | $10^6 - 10^9$ Ohm |
| Heat Resistance | 260°C |
| Backing | Polyimide Film |
| Adhesive System | Silicone |

All product properties are measured in accordance with Pressure Sensitive Tape Council and/or ASTM test methods. The physical properties listed above are typical values and are not to be construed as specifications. Our suggestions and recommendations for use are based on tests we believe to be reliable. However, the purchaser must determine the suitability of the product for his intended use. We assume no liability for claims beyond the replacement value of our product proved to be defective. Note: Tape should be stored in its original packaging in a cool, dry area (27 C to 35 C and 60% relative humidity) away from direct sunlight. Tape should be used within 12 months from the date of shipment. Application surfaces should be clean, dry and free of grease, oil or other contaminants.

VIETAPE MATERIAL TECHNOLOGY CO., LTD

18F Tang Nhon Phu Street, Phuoc Long B District,
Thu Duc City, Ho Chi Minh City, Vietnam

info@vietape.com
(+84) 869 681 639

www.vietape.com

