

EN Technical Data Sheet

Bectron®

SK 75V1-35 / SH 79V2-35

1:1

Electronic 2 Part Silicone Potting Compound

ELANTAS Europe Sales offices:

Strada Antolini, 1
43044 Collecchio (PR)
Italy
Tel +39 0521 304777
Fax +39 0521 804410

Grossmannstrasse 105
20539 Hamburg
Germany
Tel +49 40 78946 0
Fax +49 40 78946 349

Via San Martino, 6
15028 Quattordio (AL)
Italy
Tel +39 0131 773870
Fax +39 0131 773875

Keate House
1 Scholar Green Road - Cobra Court
Manchester M32 0TR
United Kingdom
Tel +44 161 864 1689
Fax +44 161 864 6090

info.elantas.europe@altana.com
www.elantas.com/Europe

Area of application

Thanks to its elastic properties and long term thermal resistance Bectron® SK 75V1-35 system is successfully used for encapsulation of pressure sensitive devices as well as for protection of motor windings in hot air systems.

Additionally Bectron® SK 75V1-35 system is generally suited as a protection for electronic components and circuits such as as high-performance semi-conductors and high load resistors.

Processing methods

Pre-treatment: The components to be treated should be clean dry and free from grease.

Compatibility between the resin and all materials of the component should be checked prior to use.

Bectron® SK 75V1-35 and cross linker Bectron® SH 79V2-35 contain filler materials which tend to settle and must be stirred in the original containers to restore the homogenous composition before processing.

Mixing: The two components should be mixed in the prescribed ratio. Care should be taken because air may be included during mixing. Brief application of vacuum can be used to remove air bubbles. Equipment must be kept clean and care is needed to avoid cross-contamination of components, which may cause hardening in the equipment after days or weeks of use.

Application: Bectron® SK 75V1-35 system can be applied either manually or with suitable mixing and dosing equipment.

Recommended curing conditions:

- 30 min at 90°C

To obtain maximum adhesion fastly, higher temperatures are recommended, for example

- 1 hour at 120°C

All vessels, pipes and equipment used must be thoroughly cleaned because the Pt catalyst of this system may be easily poisoned by traces of sulphur compounds, amines or tin salts. This would seriously inhibit the cross-linking reaction.

Description

Bectron® SK 75V1-35 when mixed with Bectron® SH 79V2-35 will cure to a self-bonding silicone rubber in 1 hour at a temperature of 120°C . Elasticity and dielectric properties of the final rubber remain largely stable in a wide range of temperatures, between -40°C and +200°C.

A 1:1 mixing ratio allows easy and safe processing of the system.

Key Properties

- Addition cure system
- Good adhesion to various materials
- Low viscosity
- Good temperature cycling resistance
- UL 94 V0

Storage and Usable Life

Products should be stored in their original sealed containers to avoid any potential contamination at a temperature below 35°C. Store accordingly to any specific instruction listed on the product label. Products should be used prior to the expiring date marked on the label.

Handling precautions

The system is RoHS compliant. Refer to the safety data sheet and comply with local regulations relating to industrial health and waste disposal.

SYSTEM SPECIFICATIONS

Property	Conditions	Method	Bectron® SK 75V1-35	Bectron® SH 79V2-35	Units
Viscosity	25°C	DIN 53019	700 ÷ 1100	875 ÷ 1275	mPas
Specific gravity	20°C	EN/DIN/ISO 2811-1	1.17 ÷ 1.27	1.19 ÷ 1.29	g/ml

TYPICAL SYSTEM CHARACTERISTICS

Property	Bectron® SK 76V1-35	Bectron® SH 79V2-35
Colour	White	Beige
Shelf Life	12 months	12 months

TYPICAL CHARACTERISTICS OF THE MIX

Mixing Ratio (parts by weight)	1:1
Viscosity of mixture @ 25°C [mPas]	990
Working Time at Room Temperature [min]	180

TYPICAL MECHANICAL PROPERTIES OF THE CURED PRODUCT

Test	Value
Specific Gravity @ 20°C [g/cm³]	1.23
Hardness [Shore A]	35

TYPICAL THERMAL PROPERTIES OF THE CURED PRODUCT

Test	Value
Thermal Conductivity [W/m*K]	0,30
UL 94 classification (5mm)	V0 (Internal Test Only)

TYPICAL DIELECTRIC PROPERTIES OF THE CURED PRODUCT

Test	Value
Dielectric Strength [KV/mm]	30
Dielectric Constant 50 Hz, 1000 Hz, 10000Hz	3.3 at 20 °C

Our advice given verbally or in writing is based on the present state of our technical knowledge, but is intended as information given without obligation, also with respect to any protective rights held by third parties. It does not relieve your own responsibility to check the products for their suitability to the purposes and processes intended and in accordance with the technical sheets of the products. The application usage and

processing of the product are beyond our control and will completely fall into the scope of responsibility of buyers and users. Should there nevertheless be a case of liability from our side, this will be limited to any damage equivalent to the value of the merchandise delivered by us. Naturally, we assume responsibility for the unobjectionable quality of our products, as defined in our general terms and condition