



TECHNICAL BULLETIN #3123 – INSULGEL 70CC FR NS
SEMI-FLEXIBLE, LOW C.T.E., EPOXY COMPOUND, SUPERIOR THERMAL SHOCK
RESISTANCE, UL 94 V-0

Revised: 11/2019

PRODUCT DESCRIPTION

INSULGEL 70 CC FR NS is an epoxy compound which exhibits superior thermal shock resistance by making use of an inherently flexible epoxy resin and special filler technology. It provides reduced shrinkage and low coefficient of thermal expansion resulting in decreased stress and improved adhesion. In addition, a significant portion of the product is manufactured from environmentally sustainable raw materials. **INSULGEL 70 CC FR NS** is UL recognized under file E86165 & meets the flammability requirement of 94 V-0.

PROPERTIES UNCURED

	PART A	PART B	
COLOR, VISUAL	Black	Amber	-
VISCOSITY @ 25°C, cps	16,000	125	ASTM D 2393
SPECIFIC GRAVITY	1.61	0.98	-
MIX RATIO (by wt.)	100:10-11		-
MIXED VISCOSITY, cps	3,000		-
POT LIFE (100 gr) @ 25°C, hrs	0.5-0.75		-
SHELF LIFE @ 25°C, months	12	12	-

PROPERTIES CURED

PHYSICAL		
HARDNESS, DUROMETER (Shore D)	50	ASTM D 2240
TENSILE STRENGTH, psi	1,200	ASTM D 638
TENSILE ELONGATION, %	90	ASTM D 638
COEFFICIENT OF THERMAL EXPANSION, °C	90x10 ⁻⁶	-
THERMAL CONDUCTIVITY, BTU-in/(ft ²)(hr)(°F)	3.6	-
THERMAL CONDUCTIVITY, W/m °K	0.518	-
SERVICE TEMPERATURE, °C:	-40 to +105	-
GLASS TRANSITION TEMPERATURE, °C	4 to 9	-

ELECTRICAL

DIELECTRIC STRENGTH, volts/mil	400	ASTM D 149
DIELECTRIC CONSTANT, 1 KHz	4.1	ASTM D 150
DISSIPATION FACTOR, 1 KHz	0.08	ASTM D 150
VOLUME RESISTIVITY, ohm-cm: @25°C	7 x 10 ¹²	ASTM D 257
VOLUME RESISTIVITY, ohm-cm: @100°C	10 ¹⁰	ASTM D 257

USE INSTRUCTIONS

1. Premix **INSULGEL 70 CC FR NS** base in original container being certain to re-incorporate any fillers that may have settled during shipment or storage. Due to the nature of the fillers, settling may be difficult to re-mix without the use of mechanical agitation or drum rollers.
2. Weigh out amount of **INSULGEL 70 CC FR NS** required.
3. Weigh out appropriate amount of curing agent.
4. Mix both materials thoroughly, being certain to carefully scrape sides and bottom of container to insure homogenous mix.
5. For absolutely void-free casting, evacuate for 5-10 minutes @29" Hg.

CURE SCHEDULE

Room temperature (25°C) - 16 to 24 hours

STORAGE REQUIREMENTS

**This product will settle upon shipment or storage.
The product should be re-mixed well prior to use.
Store material in a cool dry place.**

IMPORTANT:

The following supersedes any provision in your company's forms, letters and papers. ITW PERFORMANCE POLYMERS makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL ITW PERFORMANCE POLYMERS BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. The sole liability of ITW PERFORMANCE POLYMERS for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in ITW PERFORMANCE POLYMERS sole opinion, to justify such refund.

HEALTH CAUTION:

Avoid breathing possible fumes, mists and vapors which can cause severe respiratory damage. Use of NIOSH approved breathing apparatus is required for more than minimal exposure. Always work in areas with adequate ventilation to allow dissipation of polyamine and other chemical fumes, and where applicable, solvent fumes. Use of goggles, protective garments, rubber gloves, protective cream is required. If material gets into eyes, flush thoroughly with clean water for twenty (20) minutes; then seek medical treatment. Avoid skin contact. Material can cause contact dermatitis. Always wash exposed areas immediately, using warm water and soap, followed by rinsing with clean water. Observe all safety precautions, It is important when using solvent based materials or solvents to keep away from open flame or ignition source.

PLEASE REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER FIRST AID INFORMATION. FOR CHEMICAL EMERGENCY, CALL CHEMTREC (DAY OR NIGHT) 800 424-9300.

