



TECHNICAL BULLETIN #3030 – INSULCAST 504 CASTING EPOXY

Revised: 11/2019

PRODUCT DESCRIPTION

INSULCAST 504 is an unfilled 100% solids epoxy resin casting or impregnating material. The product has excellent physical and electrical properties.

PROPERTIES UNCURED

	INSULCAST 504	INSULCURE 9	INSULCURE 11B	
COLOR, VISUAL	Black	Amber	Amber	-
VISCOSITY, @ 25°C, cps	700	55	700	ASTM D 2392
SPECIFIC GRAVITY	1.13	0.97	0.95	-
MIX RATIO (by weight)		100:12	100:18	-
MIXED VISCOSITY @ 25°C, cps		200	300	ASTM D 2393
POT LIFE @ 25°C, 100 grams		45 mins.	5 hrs.	-
SHELF LIFE @ 25°C, months	12	12	12	-

PROPERTIES CURED

PHYSICAL	INSULCURE 9	INSULCURE 11B	
HARDNESS, DUROMETER (Shore D)	75	85	ASTM D 2240
TENSILE STRENGTH, psi	10,700	11,000	ASTM D 638
TENSILE ELONGATION, %	4.5	5.0	ASTM D 638
COMPRESSIVE STRENGTH, psi	14,000	15,600	ASTM D 695
FLEXURAL STRENGTH, psi	17,500	18,000	ASTM D 790
IZOD IMPACT, ft lbs/inch of notch	0.2	0.2	-
COEFFICIENT OF THERMAL EXPANSION, °C	61x10 ⁻⁶	75x10 ⁻⁶	-
THERMAL CONDUCTIVITY, BTU-in/(ft ²)(hr)(°F)	1.6	1.6	-
HEAT DISTORTION POINT, °C	75	155	-
SERVICE TEMPERATURE, °C	-40 to +105	155	-

ELECTRICAL

DIELECTRIC STRENGTH, volts/mil	425	435	ASTM D 149
DIELECTRIC CONSTANT, 1 KHz	4.0	4.2	ASTM D 150
DISSIPATION FACTOR, 1 KHz	0.022	0.01	ASTM D 150
VOLUME RESISTIVITY, ohm-cm	5x10 ¹⁵	1x10 ¹⁵	ASTM D 257

USE INSTRUCTIONS

1. Weigh out required amount of **INSULCAST 504** and add:
12 parts **INSULCURE 9** per 100 parts **INSULCAST 504**, OR
18 parts **INSULCURE 11B** per 100 parts **INSULCAST 504**
2. Mix curing agent in thoroughly, scraping both the sides and bottom of the container to insure proper blending.
3. Evacuate for 2-5 minutes if void-free castings are required.
4. Pour into cavity or mold, etc.

CURE SCHEDULE

INSULCURE 9: At room temperature (25°C.) for 8-12 hours
Full properties after 24 hours

INSULCURE 11B: Masses 1/2 lb. or under - 2 hours at 70°C.
Post Cure - 2 hours at 100°C.
Masses to 2 lbs. - 2 hours at 60°C.
Post Cure - 2 hours at 100°C
Masses over 2 lbs. overnight at room temp. (25°C)
Post Cure - 2 hours at 75°C or 1 hour at 100°C.

IMPORTANT:

The following supersedes any provision in your company's forms, letters and papers. ITW PERFORMANCE POLYMERS makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL ITW PERFORMANCE POLYMERS BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. The sole liability of ITW PERFORMANCE POLYMERS for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in ITW PERFORMANCE POLYMERS sole opinion, to justify such refund.

HEALTH CAUTION:

Avoid breathing possible fumes, mists and vapors which can cause severe respiratory damage. Use of NIOSH approved breathing apparatus is required for more than minimal exposure. Always work in areas with adequate ventilation to allow dissipation of polyamine and other chemical fumes, and where applicable, solvent fumes. Use of goggles, protective garments, rubber gloves, protective cream is required. If material gets into eyes, flush thoroughly with clean water for twenty (20) minutes; then seek medical treatment. Avoid skin contact. Material can cause contact dermatitis. Always wash exposed areas immediately, using warm water and soap, followed by rinsing with clean water. Observe all safety precautions. It is important when using solvent based materials or solvents to keep away from open flame or ignition source.

PLEASE REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER FIRST AID INFORMATION. FOR CHEMICAL EMERGENCY, CALL CHEMTREC (DAY OR NIGHT) 800 424-9300.