

TEROSON PU U632/U152

Known as BONDMASTER U632/U152

September 2015

PRODUCT DESCRIPTION

Technology	Polyurethane, 2-component
Product Type	semi structural adhesive
Additional Information	elastic

TEROSON PU U632/U152 is a polyurethane based two-component adhesive which cures at room temperature. For accelerated curing it is recommended to use a heat source.

APPLICATION AREAS

TEROSON PU U632/U152 is used in the automotive industry by Headlight manufacturers for bonding lens to body. For any other substrate please ask our technical advice.

TECHNICAL DATA (Typical Test Results)

COMPONENT A (Polyol)

Colour	black
Density	approx. 1.6 g/cm ³
Solids	>99 %
Viscosity Brookfield RVT	approx. 150,000 mPa.s
Equipment	Spindle 7; 20 rpm
Temperature	23°C

COMPONENT B (Isocyanate)

Colour	black
Density	approx. 1.3 g/cm ³
Solids	>99 %
Viscosity Brookfield RVT	approx. 22,000 mPa.s
Equipment	Spindle 6; 10 rpm
Temperature	23°C

Mixing ratio A : B

by weight	100 : 18
by volume	100 : 21.3

MIXTURE (Component A + B)

Potlife (60 g, 23°C)	approx. 3 min(s)
Shear strength, 23°C after 7 d curing	1.5 MPa

PRELIMINARY STATEMENT

Prior to application it is necessary to read the Safety Data Sheet for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed.

DIRECTIONS OF USE

Pretreatment

The parts to be bonded must be free from oil, grease, moisture, dirt and release agents. From the Henkel portfolio for example TEROSON PU 8550 or TEROSON VR 20 can be used as cleaners. In the case of plastics a flame pre-treatment like plasma or corona can be necessary to ensure good adhesion of TEROSON PU U632/U152 to the substrate. Occasionally usage of a primer is also an option.

Application

Apply using a meter mix pump. Product is temperature sensitive with a short pot life. Use only static mix head. Extrude a bead on one of the substrates to be bonded. Position rapidly second substrate and apply a light pressure for several minutes. Do not mix with other products. Purge and rinse mix head regularly to avoid fouling. To ensure proper mixing, static mixers with at least 24 mixing elements are required. For any other applying condition, please ask for our technical advice.

Curing

Curing occurs at room temperature. At the beginning curing should occur under fixation of the substrates to avoid shifting of the parts to be bonded (especially in the case of tension between the joint partners). The rate of cure is temperature-dependent and influences open time and time to handling strength. Higher temperatures accelerate, lower temperatures slow down the curing speed. For accelerated curing it is recommended to increase the temperature up to 60 to 70 °C. Final strength is widely reached after 3 days at room temperature.

Cleaning

Freshly applied and uncured material should be removed with a dry cloth or using a solvent as TEROSON VR 40 or MEK. Cured adhesive can only be removed mechanically.

TEROSON PU U632/U152

September 2015

STORAGE

TEROSON PU U152

Frost sensitive	yes
Recommended storage temperature	5 to 25 °C *
Shelf life	6 months

A sufficient agitation is always recommended just before use to eliminate any possible phase separation on top of the product. For the agitation we recommend to place the full closed pail during 5 minutes in a gyroscopic mixer or in a portable drum roller. After homogenization the most appropriate is to use the product within 48 hours.

* or 5°C to 35°C if a "bi-axial gyroscopic" agitation is made just before use.

TEROSON PU U632

Frost sensitive	yes
Recommended storage temperature	5 to 35°C
Shelf life	8 months

Avoid moisture.

Ensure a good rotation of stocks by using oldest material first.

Disclaimer

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out

your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Henkel AG & Co. KGaA

D-40191 Düsseldorf, Germany
Phone: +49-211-797-0
www.henkel.com

Henkel Central Eastern Europe GmbH

A-1030 Wien, Austria
Phone: +43-1711-040
www.henkel.com

Henkel & Cie AG

CH-4133 Pratteln, Switzerland
Phone: +41-61-825-7000
www.henkel.com

