

SILTRUST™ RTV8111, RTV8112, RTV8262 SILICONE RUBBER COMPOUNDS

Product Description

SILTRUST RTV8111, RTV8112 and RTV8262 silicone rubber compounds are two- part silicone elastomers supplied in ready-to-use matched kits containing a base compound and curing agent.

Key Features and Typical Benefits

- Conforms to the physical and electrical requirements of MIL-S-23586E
- Non-corrosive to copper
- Retention of elastomeric properties at high temperature up to 204°C (400°F) continuously for RTV8111 and RTV8112 up to 260°C (500°F) continuously for RTV8262
- Excellent adhesion capabilities when used with primer
- Room temperature cure
- Composition free of solvents

Typical Physical Properties

UNCURED PROPERTIES OF RTV BASE COMPOUNDS	RTV8111	RTV8112	RTV8262
Color	White	White	Red
Consistency	Easily Pourable	Easily Pourable	Pourable
Viscosity, cps	9900	11,000	47,000
Specific Gravity	1.18	1.19	1.47

TYPICAL PROPERTIES OF CURING AGENTS	RTV9891	RTV9858
Color	Light Blue	Off-White
Consistency	Pourable	Pourable
Viscosity, cps	170,000	44,000
Specific Gravity	1.77	1.61
Active Catalyst	STO	DBT

Typical properties are average data and are not to be used as or to develop product specifications.

TYPICAL UNCURED PROPERTIES WITH CURING AGENT ADDED	RTV8111 / RTV9891	RTV8112 / RTV9858	RTV8262 / RTV9858
Curing Agent Added, weight %	2 - 4	5 - 7	5 - 7
Pot Life @ 25°C (77°F) hours	0.5	2	2
Cure Time @ 25°C (77°F) hours	24	24	24
TYPICAL CURED PROPERTIES (Cured 72 hours @ 25°C (77°F) and 50% R.H.)	RTV8111	RTV8112	RTV8262
Mechanical			
Hardness, Shore A Durometer	45	42	52
Tensile Strength, kg/cm ² (psi)	25 (350)	21 (300)	41 (580)
Elongation, %	160	160	150
Tear Strength, kg/cm (lb/in)	4.3 (24)	4.8 (27)	7.7 (43)
Linear Shrinkage, %	1.0	1.0	0.6
Electrical			
Dielectric Strength, kv/mm (v/mil) (1.9 mm thick)	19.7 (500)	18.7 (475)	18.5 (470)
Dielectric Constant @ 103 Hz	3.3	4.02	3.98
Dissipation Factor @ 103 Hz	0.0055	0.007	0.017
Volume Resistivity, ohm-cm	1 x 10 ¹⁵	2.7 x 10 ¹⁵	4.4 x 10 ¹⁴
Thermal			
Useful Temperature Range, °C (°F)	-54 to 204 (-65 to 400)	-54 to 204 (-65 to 400)	-54 to 260 (-65 to 500)
Thermal Conductivity (W/m-K)	0.29	0.29	0.29
Coefficient of Linear Expansion, cm/(cm°C), (in/(in°F))	25 x 10 ⁻⁵ (14 x 10 ⁻⁵)	25 x 10 ⁻⁵ (14 x 10 ⁻⁵)	20 x 10 ⁻⁵ (11 x 10 ⁻⁵)
Specific Heat, cal/(gm°C) , (BTU/lb, °F)	0.35 (0.35)	0.35 (0.35)	0.35 (0.35)
MIL-S-23586E SPECIFICATION LIMITS (Cured 72 hours @ 23 ± 2°C and 50% ± 5% R.H.)	Type I, Class 1 Grade B1	Type I, Class 2 Grade A	Type II, Class 2 Grade A
Suggested Momentive Performance Materials Product	RTV8111	RTV8112	RTV8262
Viscosity, cps	20,000 max	20,000 max	20,000 - 200,000

Pot Life, hours	0.25 - 0.75	1 - 3	1 - 3
Hardness, Shore A Durometer, min	40	35	45
Tensile Strength, kg/cm ² (psi), min.	17.6 (250)	17.6 (250)	22.9 (325)
Elongation, %, min.	100	100	100
Dielectric Strength, kv/mm (v/mil), min.	15.7 (400)	15.7 (400)	15.7 (400)

Potential Applications

Typical applications include, but are not limited to the potting of electronic circuit modules, electrical connectors and coils, and other applications in electronics, military/defense and commercial aerospace industries.

Processing Recommendations

Prior to measuring the needed RTV base material, ensure the material is homogeneous. Incorporate any material at the bottom of the container using clean hand tools such as a metal spatula. Mix until the RTV base material is uniform in feel and thickness.

Select a mixing container 4 to 5 times larger than the volume of RTV silicone rubber compound to be used. Weigh out the RTV silicone rubber base compound and add the appropriate amount of curing agent. Using clean tools, thoroughly mix the RTV base compound and the curing agent, scraping the sides and bottom of the container carefully to produce a homogeneous mixture. When using power mixers, avoid excessive speeds which could entrap large amounts of air or cause overheating of the mixture, resulting in shorter pot life.

Deaeration

Air entrapped during mixing should be removed to eliminate voids in the cured product. Expose the mixed material to a vacuum of about 25 mm (29 inches) of mercury. The material will expand, crest, and recede to about the original level as the bubbles break. Degassing is usually complete about two minutes after frothing ceases. When using the RTV silicone rubber compound for potting, a deaeration step may be necessary after pouring to avoid capturing air in complex assemblies.

Instead of the above procedure, because of the short pot life of RTV8111/RTV9891 mixtures, mixing under vacuum or using a static mixer may be necessary to eliminate trapped air.

Curing

Using the curing agent levels prescribed, RTV8111, RTV8112 and RTV8262 silicone rubber compounds will cure in 24 hours at 25°C (77°F) and 50% relative humidity to form durable, resilient rubbers. Pot life of catalyzed compounds may be lengthened by refrigeration. Slight adjustments to the pot life and cure rate may also be made by changing the curing agent levels within the limits listed in the curing agent table.

Bonding

If adhesion is an important application requirement, RTV8111, RTV8112 and RTV8262 silicone rubber compounds require a primer to bond to non-silicone surfaces. Clean the substrate thoroughly with a non-oily solvent such as naphtha or methyl ethyl ketone (MEK) and let dry. Then apply a uniform thin film of a suitable silicone primer such as SS4004P. Allow the primer to air dry for one hour or more. Apply freshly catalyzed RTV silicone rubber compound to the primed surface and cure as recommended.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement, or recommendation to practice any invention covered by any patent without authority from the owner of the patent.

Product Safety, Handling, and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling

instructions, personal protective equipment, if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular application(s).

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas

+1 800 295 2392
Toll free*
+704 805 6946
Direct Number

*All American countries

Latin America

Brazil
+55 11 4534 9650
Direct Number

Mexico
+52 55 2169 7670
Direct Number

EMEA- Europe, Middle East, Africa & India

Europe
+390510924300
Direct number

India, Middle East & Africa
+ 91 44 71212207
Direct number*

*All Middle Eastern countries, Africa, India, Pakistan, Bangladesh, Sri Lanka.

ASIA PACIFIC

China
800 820 0202
Toll free
+86 21 3860 4892
Direct number

Japan
Email
Sales-JP.Silicones@momentive.com

Korea
+82 2 6201 4600
Direct number

South East Asia, Australia & New Zealand
+60 3 8309 8088
Direct number*

*South East Asia countries (Malaysia, Singapore, Thailand, Indonesia, Vietnam, Philippines, Cambodia, Myanmar / other countries located in Pacific region).

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS, AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS, INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER") ARE SOLD SUBJECT TO SUPPLIER'S

STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS, OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service, or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design or as a recommendation for the use of such material, product, service, or design in the infringement of any patent or other intellectual property right.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials, Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials, Inc.



2750 Balltown Road,
Niskayuna
NY 12309 USA
momentive.com

Copyright 2025 Momentive Performance Materials, Inc. All rights reserved. Latest revision on October 8, 2025