

SILTRUST™ RTV834 TWO PART TACKY SILICONE RUBBER

Description

SILTRUST RTV834 is a solvent-free, flowable, two component tacky RTV silicone rubber. After mixing the RTV834A and RTV834B at a mix ratio of 1:1 the material cures by an addition reaction at room temperature. The cure rate can be accelerated significantly by heat. Material has been specially developed as a tacky fabric coating.

Key Features and Typical Benefits

- Convenient 1:1 mixing Free of solvents
- Good self leveling characteristics No by-products released
- Fast cure at elevated temperatures Translucent

Typical Physical Properties

<u>Property</u>	<u>Unit</u>	<u>Value</u>	
Uncured Properties			
		A-part	B-part
Color		Translucent	Translucent
Viscosity at 20 °C	Pa·s	130	90
Mix ratio by weight		1	1
Typical Catalyzed Properties			
Pot Life at 23 °C	minutes	100	
Density	g/cm ³	1.05	
Hardness	Shore 00	40	
Tensile Strength	MPa	2	
Modulus 100%	MPa	0.15	

Elongation	%	500
------------	---	-----

Typical physical properties are average data and should not be used as or to develop product specifications. Properties were obtained on 2 mm thick ASTM sheets. The sheets were press-cured for 10 minutes at 175 °C

Potential Applications

SILTRUST RTV834 tacky silicone compound has been specially developed as a tacky coating for fabric requiring repositionable adhesive properties. Typical applications include, but are not limited to, lace coating, clothes and conveyer belt coating. SILTRUST RTV834 can also be used for other applications where fast cure at elevated temperatures with a tacky surface and good flow or self-leveling characteristics are required.

General Specifications

Typical product data values should not be used as specification. Assistance and specifications are available by contacting Momentive Performance Materials' technical service RTV.

Instructions For Use Mixing

Select a mixing container 4-5 times larger than the total volume of material to be mixed. Weigh out the RTV834A and RTV834B components (in a ratio of 1:1 by weight) optionally combined with a pigment paste (e.g. 1 or 2 percent by weight of Silopren LSR color batch). Stir for several minutes until the material is well mixed. The air entrapped in the mixing steps needs to be removed. Exposing the material to an absolute pressure of 10-20 mbar will achieve this. The material will expand, crest and reduce to approximately its original level. Degassing is usually complete within about two minutes after frothing ceases. Automatic equipment designed to meter, mix and dispense a two component silicone liquid rubber, with optionally a third system to dose and mix in the pigment, will add convenience to continuous large scale operations.

Compatibility

SILTRUST RTV834 will cure when applied to a clean, dry surface, which has been properly prepared. Certain materials such as butyl and chlorinated rubber, sulfur containing materials, amines and certain metal soap-cured RTV silicone rubber compounds, can cause cure inhibition.

It is recommended that a sample patch test will be performed with the RTV product to determine if a barrier coating or other inhibition preventing measure is necessary before applying the SILTRUST RTV834.

Curing

Thin coatings of RTV834 can be applied to the substrate by dipping, knife spreading or extrusion. Thin films can be cured within two minutes at 150 °C depending on coat weight and heat exchange efficiency. Thicker coatings will decrease the rate of heat transfer and will therefore require a longer cure time or higher cure temperature.

Bonding

Due to the excellent flow and penetration behavior of SILTRUST RTV834 mechanical bonding is obtained on most fabrics. If a stronger (chemical) bond is required, then the use of a primer will be needed. A suitable primer is SS4155 or SS4120. The surface of the substrate to be primed needs to be thoroughly cleaned. Cleaning should be done with a non-oily solvent such as MEK or IPA. The primer needs to be applied in a uniform thin layer on the cleaned surface. Allow the primer to dry for one hour or more. Apply the freshly mixed SILTRUST RTV834 to the primed surface and cure as recommended.

To confirm the bonding performance, it is recommended to do a small-scale adhesion test on the substrate.

Containers

Material is available in 40 kg pail kits and in 400 kg drum kits.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product

storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392 Toll free* +704 805 6946 Direct Number	Brazil +55 11 4534 9650 Direct Number	Europe +390510924300 Direct number	China 800 820 0202 Toll free +86 21 3860 4892 Direct number
All American countries	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207 Direct number	Japan +81 3 5544 3111 Direct number
		*All Middle Eastern countries, Africa, India,	Korea +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the “™” symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.