

SNAPSIL TSE325™ SILICONE ADHESIVE

Description

SNAPSIL TSE325 silicone adhesive is a one-component heat curable silicone adhesive designed for potting and encapsulation. This product cures at elevated temperatures and adheres to many substrates without a primer. SNAPSIL TSE325 is a white, flowable material with self-leveling properties.

Key Features and Typical Benefits

- One component products - no mixing required
- Cure at elevated temperature
- Low viscosity - easily pourable
- Primerless adhesion to many types of substrates
- No cure by-products, low linear shrinkage
- Non-corrosive to metals and sensitive substrates

Typical Physical Properties

<u>Property</u>	<u>Unit</u>	<u>Value</u>
Uncured Properties		
Colour		White
Viscosity (23 °C)	Pa·s	4
Cured Properties (1 hour at 150 °C)		
Density	g/cm ³	1.02
Hardness (Type A)		12
Elongation	%	200
Tensile Strength	MPa	0.7
Adhesion (Al to Al)	MPa	0.4

Dielectric Strength	kV/mm	21
Dielectric Constant (60Hz)		2.9
Dissipation Factor (60Hz)		0.001
Volume Resistivity	$\Omega \cdot \text{cm}$	2×10^{15}

Typical properties are average data and should not be used as or to develop product specifications.

Potential Applications

- Coating of hybrid IC's, printed circuit boards, etc
- Electrical potting and encapsulation
- General adhesive for many types of substrates

Processing Recommendations

Compatibility

SNAPSIL TSE325 silicone adhesive cures in contact with most clean, dry surfaces. However, certain materials, such as butyl and chlorinated rubber, sulfurcontaining materials, amines, and certain metal soap cured RTV silicone rubber compounds can cause cure inhibition. Cure inhibition is characterized by a gummy appearance of the SNAPSIL TSE325 silicone adhesive at the interface between the adhesive and the substrate to be bonded. It is recommended that a sample patch test be performed with the SNAPSIL TSE325 silicone adhesive to determine substrate compatibility.

Surface Preparation

The adhesive performance of any polymer system is highly dependent upon proper surface preparation. In order to maximize the adhesion of TSE325 silicone adhesive and minimize the potential for cure inhibition, all parts should be as clean and dry as possible prior to the application of the adhesive.

Curing

SNAPSIL TSE325 silicone adhesive requires elevated temperatures in order to achieve full cure. Typical cure times and temperatures are as follows:

Temperature	Cure Time
100 °C	4 hours
120 °C	2 hours
150 °C	1 hour

Note: Test data. Actual results may vary.

The actual cure time is affected by such things as cross-sectional thickness of the SNAPSIL TSE325 silicone adhesive, heat capacity of the overall assembly and efficiency and type of oven used (i.e. convection, infrared)

Adhesion capability

Suitable substrates

Metals: Aluminium, Copper, Ni plate; Stainless steel

Plastics: PPS, PBT, Epoxy resin, Polyester, Phenolic resin

Rubbers: Heat cured silicone rubber

Inorganics: Glass, Ceramics

Not suitable substrates

Plastics: PP, PE, Fluorocarbon resin

Rubbers: Sulphur vulcanized rubbers, Fluorocarbon rubber

Specifications

Typical product data values should not be used as specifications. Assistance and specifications are available by contacting Momentive Performance Materials Technical Service RTV1 and RTV2.

Availability

SNAPSIL TSE325 is available in 1kg cans and 18 kg pails.

General Considerations for Use

While the typical operating temperature for silicone materials ranges from -45°C to 200°C, the long-term maintenance of its initial properties is dependent upon design related stress considerations, substrate materials, frequency of thermal cycles, and other factors.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product

safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392 Toll free*	Brazil +55 11 4534 9650 Direct Number	Europe +390510924300 Direct number	China 800 820 0202 Toll free +86 21 3860 4892 Direct number
+704 805 6946 Direct Number	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207 Direct number*	Japan +81 3 5544 3111 Direct number
*All American countries		*All Middle Eastern countries, Africa, India,	Korea +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the “™” symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.